

# A Three-dimensional Tm(III)-Zn(II) Heteronuclear Metal-organic Framework Based on Imidazole-dicarboxylate Ligand: Synthesis, Crystal Structure and Luminescence Property

GUO Nan<sup>(1)</sup>(郭楠); FENG Xun<sup>(2)</sup>(冯勋); JIA Hong<sup>c</sup>(贾红); QIN Guo-Zhan<sup>(2)</sup>(秦国展); WEI Jing-Tao<sup>(2)</sup>(魏靖涛); HAN Zhi-Yue<sup>(2)</sup>(韩志越)

<sup>(1)</sup> College of Chemistry and Molecular Engineering, Zhengzhou University, Zhengzhou 450001, China; <sup>(2)</sup>

College of Chemistry and Chemical Engineering and Henan Key Laboratory of Function Oriented Porous Materials, Luoyang Normal University, Luoyang 471934, China; <sup>(3)</sup> College of Physics, Luoyang Normal University, Luoyang 471934, China

**ABSTRACT** A *d-f* heteronuclear metal-organic framework (MOF),  $\{[\text{Tm}_3\text{Zn}_6(\text{bipy})_2(\text{mimda})_7(\text{H}_2\text{O})_3](\text{H}_2\text{O})_5\}_n$  (**1**,  $\text{H}_3\text{mimda}$  = 2-methyl-1-H-imidazole-4,5-dicarboxylic acid, and  $\text{bipy}$  = 4,4'-bipyridine), has been synthesized under solvothermal conditions, and structurally characterized by elemental analysis, IR spectra and X-ray single-crystal diffraction. It crystallizes in orthorhombic system, space group *Pnma* with  $a = 16.1102(9)$ ,  $b = 33.5805(19)$ ,  $c = 16.8593(10)$  Å,  $\beta = 97.344(11)^\circ$ ,  $V = 9120.7(9)$  Å<sup>3</sup>,  $Z = 4$ ,  $F(000) = 5184$ , the final  $R = 0.0530$  and  $wR = 0.1306$ . In complex **1**, the Tm(III) ions adopt two types of coordination fashions. Complex **1** shows one-dimensional (1-D) Tm-Zn heteronuclear zigzag chains, and these chains are further linked by  $\text{H}_3\text{mimda}$  ligands into Tm-Zn heteronuclear 2-D lattice-like arrays. The 2-D heteronuclear units were connected through  $[\text{Zn}_6(\text{mimda})_6]$  rings to give rise to the Tm-Zn heteronuclear cages. Finally,  $\text{H}_3\text{mimda}$  ligands connected the cages into a 3-D heterometallic framework by the combination of  $[\text{TmO}_7]_n$  and Tm-Zn heteronuclear cages. In addition, the thermal stability and luminescent property have been investigated.

**Keywords:** *d-f* heteronuclear metal-organic frameworks; Tm(III) complex; 2-methyl-1-H-imidazole-4;5-dicarboxylic acid; luminescence;

DOI: 10.14102/j.cnki.0254-5861.2011-1658

## 1 INTRODUCTION

In recent years, lanthanide-based metal-organic frameworks (MOFs) have increasingly attracted considerable attention because of their intriguing structural topologies and potential applications in gas storage, luminescence and magnetism<sup>[1-6]</sup>. Lanthanide metal ions possess high coordination numbers and the long wavelengths range from the visible to the near-infrared region. However, the absorption coefficients are

usually very low with slow emissive rates due to the Laporte forbidden  $f-f$  transitions<sup>[7, 8]</sup>. In order to reduce the effect of this problem, our strategy is to employ the imidazole dicarboxylate ligand as chromophores and transition metal that can improve the energy transition<sup>[9-11]</sup>. The imidazole dicarboxylate ligands containing N and O donors are especially popular because they can adopt a variety of coordination modes, which has proven to be an excellent building block for forming a series of MOFs with fascinating structures and useful properties. A large number of imidazole dicarboxylate-based MOFs of transition metal ions have been reported<sup>[12, 13]</sup>. On the other hand, introducing pillared rigid ligand containing N atoms such as 4,4'-bipyridine into these MOFs is another effective strategy for producing diversified structure and enhancing the performance of the final MOFs<sup>[14]</sup>. However, it is still a challenge to design and construct  $d-f$  heteronuclear MOFs<sup>[15-18]</sup> with dicarboxylate ligands due to the different reaction conditions such pH values, metal/ligand ratio, solvents, and reaction temperature. In this contribution, a new complex,  $\{[\text{TM}_3\text{Zn}_6(\text{bipy})_2(\text{mimda})_7(\text{H}_2\text{O})_3](\text{H}_2\text{O})_5\}_n$  (**1**) based on  $\text{H}_3\text{mimda}$  ligand and bipy has been obtained. In addition, the IR, photoluminescence and thermal stability of **1** have been investigated.

## 2 EXPERIMENTAL

### 2.1 Materials and physical measurements

All chemicals and solvents purchased were of reagent grade and used without further purification. Elemental analyses for carbon, hydrogen and nitrogen were carried out on a Model 240 Perkin-Elmer elemental analyzer. The infrared spectrum was performed on an IRAffinity-1S in the range of 3500~500  $\text{cm}^{-1}$ . The X-ray powder diffraction pattern (XRPD) of **1** was recorded at 293 K on a Bruker D8 Advance diffractometer ( $\text{CuK}\alpha$ ,  $\lambda = 1.54056 \text{ \AA}$ ) operated at 40 kV and 30 mA, using a Cu-target tube and a graphite monochromator. Thermal gravimetric analysis (TGA) experiments were carried out on a Perkin-Elmer Diamond SII thermal analyzer from room temperature to 1200  $^{\circ}\text{C}$  under a nitrogen atmosphere at a heating rate of 10  $^{\circ}\text{C}/\text{min}^{-1}$ . The emission/excitation spectra were recorded on an F-7000 (HITACHI) spectrophotometer at room temperature.

### 2.2 Synthesis of complex 1

A mixture of  $\text{Tm}_2\text{O}_3$  (0.05 mmol, 0.0192 g),  $\text{Zn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  (0.0370 g, 0.1 mmol),  $\text{H}_3\text{mimda}$  (0.15 mmol, 0.0270 g) and bipy (0.1 mmol, 0.0170 g) was mixed in a DMF-water solution (10 mL). After that the mixture was added into a Teflon-lined autoclave and heated to 162  $^{\circ}\text{C}$  for 5400 minutes, and then cooled to room temperature. Colorless crystals of **1** were obtained in 0.0048 g yield (48%, based on lanthanide element). Elemental Anal. Calcd. (%) for  $\text{C}_{62}\text{H}_{51}\text{N}_{18}\text{O}_{45}\text{TM}_3\text{Zn}_6$ : C, 27.91; H, 1.92; N, 9.45. Found: C, 27.95; H, 1.90; N, 9.47. IR ( $\text{cm}^{-1}$ ): 3340w, 2974m, 2897w, 2367m, 1716w, 1539m, 1388m, 1049m, 887m, 771m.

### 2.3 Crystal structure determination

A colorless block crystal of complex **1** (0.26mm  $\times$  0.21mm  $\times$  0.18mm) was mounted on a Bruker SMART APEX II CCD diffractometer equipped with a graphite-monochromatized  $\text{MoK}\alpha$  radiation ( $\lambda = 0.71073 \text{ \AA}$ ) by using a  $\varphi/\omega$  scan mode at room temperature. A total of 99936 reflections were collected for **1**, of which 10650 ( $R_{\text{int}} = 0.0837$ ) independent reflections in the range of  $1.75 \leq \theta \leq 27.50^{\circ}$  with index ranges of

$-20 \leq h \leq 20$ ,  $-43 \leq k \leq 43$  and  $-21 \leq l \leq 21$  were collected at 293(2) K. All non-hydrogen atoms were refined with anisotropic thermal parameters. The structure was solved by direct methods with SHELXS-97<sup>[19]</sup>. The hydrogen atoms were assigned with common isotropic displacement factors and included in the final refinement by use of geometrical restraints. A full-matrix least-squares refinement on  $F^2$  was carried out using SHELXL-97<sup>[20]</sup>. For complex **1**, disordered methyl carbon atoms of H<sub>3</sub>mimda ligands were restrained in order to obtain reasonable thermal parameters<sup>[21]</sup>. The final  $R = 0.0530$  and  $wR = 0.1306$  ( $w = 1/[\sigma^2(F_o^2) + (0.0406P)^2 + 146.3998P]$ , where  $P = (F_o^2 + 2F_c^2)/3$ ),  $S = 1.093$ ,  $(\Delta\rho)_{\max} = 2.776$  and  $(\Delta\rho)_{\min} = -1.150$  e/Å<sup>3</sup>. The selected bond lengths and bond angles and the hydrogen bond parameters are listed in Tables **1** and **2**, respectively.

**Table 1. Selected Bond Lengths (Å) and Bond Angles (°) for Complex **1****

Bond	Dist.	Bond	Dist.	Bond	Dist.
Tm(1)–O(1)	2.212(7)	Tm(1)–O(1)#1	2.212(7)	Tm(1)–O(5)	2.255(6)
Tm(1)–O(5)#1	2.255(6)	Tm(1)–O(3)	2.256(7)	Tm(1)–O(3)#1	2.256(7)
Tm(1)–O(1W)	2.361(10)	Tm(2)–O(11)	2.193(6)	Tm(2)–O(9)	2.226(6)
Tm(2)–O(7)	2.283(6)	Tm(2)–O(3W)	2.290(7)	Tm(2)–O(2W)	2.310(8)
Tm(2)–O(13)	2.373(5)	Tm(2)–O(13)#2	2.473(5)	Tm(2)–O(14)#2	2.486(5)
Tm(2)–C(20)#2	2.865(7)	Zn(1)–O(4W)	1.972(10)	Zn(1)–N(2)	2.000(7)
Zn(1)–N(5)#3	2.011(7)	Zn(1)–O(4)	2.100(7)	Zn(1)–O(10)#3	2.138(7)
Zn(2)–N(1)#4	2.046(8)	Zn(2)–N(3)	2.074(7)	Zn(2)–N(6)	2.080(7)
Zn(2)–O(12)	2.171(6)	Zn(2)–O(6)	2.183(6)	Zn(2)–O(2)#4	2.229(7)
Zn(3)–N(7)	1.981(7)	Zn(3)–N(4)#5	2.002(7)	Zn(3)–N(8)	2.036(8)
Zn(3)–O(8)#5	2.126(6)	Zn(3)–O(14)	2.318(6)	O(2)–Zn(2)#6	2.229(7)
O(8)–Zn(3)#7	2.126(6)	O(10)–Zn(1)#8	2.138(7)	O(13)–Tm(2)#2	2.473(5)
O(14)–Tm(2)#2	2.486(5)				
Angle	(°)	Angle	(°)	Angle	(°)
O(1)–Tm(1)–O(1)#1	82.1(4)	O(1)–Tm(1)–O(5)	76.6(3)	O(1)#1–Tm(1)–O(5)	125.6(3)
O(1)–Tm(1)–O(5)#1	125.6(3)	O(1)#1–Tm(1)–O(5)#1	76.6(3)	O(5)–Tm(1)–O(5)#1	76.5(4)
O(1)–Tm(1)–O(3)	94.9(3)	O(1)#1–Tm(1)–O(3)	154.6(3)	O(5)–Tm(1)–O(3)	77.4(3)
O(5)#1–Tm(1)–O(3)	123.6(3)	O(1)–Tm(1)–O(3)#1	154.6(3)	O(1)#1–Tm(1)–O(3)#1	94.9(3)
O(5)–Tm(1)–O(3)#1	123.6(3)	O(5)#1–Tm(1)–O(3)#1	77.4(3)	O(3)–Tm(1)–O(3)#1	77.1(4)
O(1)–Tm(1)–O(1W)	78.8(3)	O(1)#1–Tm(1)–O(1W)	78.8(3)	O(5)–Tm(1)–O(1W)	141.7(2)
O(5)#1–Tm(1)–O(1W)	141.7(2)	O(3)–Tm(1)–O(1W)	75.9(3)	O(3)#1–Tm(1)–O(1W)	75.9(3)
O(11)–Tm(2)–O(9)	84.6(2)	O(11)–Tm(2)–O(7)	81.8(3)	O(9)–Tm(2)–O(7)	79.2(2)
O(11)–Tm(2)–O(3W)	114.2(3)	O(9)–Tm(2)–O(3W)	130.9(3)	O(7)–Tm(2)–O(3W)	145.0(2)
O(11)–Tm(2)–O(2W)	79.4(3)	O(9)–Tm(2)–O(2W)	72.6(3)	O(7)–Tm(2)–O(2W)	147.2(2)
O(3W)–Tm(2)–O(2W)	67.7(3)	O(11)–Tm(2)–O(13)	76.9(2)	O(9)–Tm(2)–O(13)	152.4(2)
O(7)–Tm(2)–O(13)	78.0(2)	O(3W)–Tm(2)–O(13)	76.0(3)	O(2W)–Tm(2)–O(13)	122.6(3)
O(11)–Tm(2)–O(13)#2	138.2(2)	O(9)–Tm(2)–O(13)#2	124.2(2)	O(7)–Tm(2)–O(13)#2	75.9(2)
O(3W)–Tm(2)–O(13)#2	71.8(2)	O(2W)–Tm(2)–O(13)#2	134.3(3)	O(13)–Tm(2)–O(13)#2	64.2(2)
O(11)–Tm(2)–O(14)#2	159.4(2)	O(9)–Tm(2)–O(14)#2	77.0(2)	O(7)–Tm(2)–O(14)#2	85.6(2)
O(3W)–Tm(2)–O(14)#2	85.3(3)	O(2W)–Tm(2)–O(14)#2	103.6(3)	O(13)–Tm(2)–O(14)#2	116.29(18)
O(13)#2–Tm(2)–O(14)#2	52.12(17)	O(11)–Tm(2)–C(20)#2	160.0(3)	O(9)–Tm(2)–C(20)#2	101.4(2)
O(7)–Tm(2)–C(20)#2	80.7(2)	O(3W)–Tm(2)–C(20)#2	76.3(3)	O(2W)–Tm(2)–C(20)#2	120.6(3)
O(13)–Tm(2)–C(20)#2	90.1(2)	O(13)#2–Tm(2)–C(20)#2	25.95(19)	O(14)#2–Tm(2)–C(20)#2	26.21(19)
O(4W)–Zn(1)–N(2)	122.8(4)	O(4W)–Zn(1)–N(5)#3	111.9(4)	N(2)–Zn(1)–N(5)#3	125.3(3)
O(4W)–Zn(1)–O(4)	91.9(4)	N(2)–Zn(1)–O(4)	80.3(3)	N(5)#3–Zn(1)–O(4)	101.3(3)
O(4W)–Zn(1)–O(10)#3	92.6(4)	N(2)–Zn(1)–O(10)#3	95.0(3)	N(5)#3–Zn(1)–O(10)#3	79.5(3)
O(4)–Zn(1)–O(10)#3	174.8(3)	N(1)#4–Zn(2)–N(3)	97.4(3)	N(1)#4–Zn(2)–N(6)	155.9(3)
N(3)–Zn(2)–N(6)	105.9(3)	N(1)#4–Zn(2)–O(12)	93.6(3)	N(3)–Zn(2)–O(12)	99.5(3)

N(6)–Zn(2)–O(12)	76.9(2)	N(1)#4–Zn(2)–O(6)	90.1(3)	N(3)–Zn(2)–O(6)	77.8(2)
N(6)–Zn(2)–O(6)	100.5(3)	O(12)–Zn(2)–O(6)	175.7(3)	N(1)#4–Zn(2)–O(2)#4	76.0(3)
N(3)–Zn(2)–O(2)#4	161.0(3)	N(6)–Zn(2)–O(2)#4	83.5(3)	O(12)–Zn(2)–O(2)#4	98.6(3)
O(6)–Zn(2)–O(2)#4	84.4(3)	N(7)–Zn(3)–N(4)#5	128.9(3)	N(7)–Zn(3)–N(8)	124.6(3)
N(4)#5–Zn(3)–N(8)	106.5(3)	N(7)–Zn(3)–O(8)#5	99.1(3)	N(4)#5–Zn(3)–O(8)#5	79.9(3)
N(8)–Zn(3)–O(8)#5	92.2(3)	N(7)–Zn(3)–O(14)	76.8(2)	N(4)#5–Zn(3)–O(14)	103.6(2)
N(8)–Zn(3)–O(14)	89.2(3)	O(8)#5–Zn(3)–O(14)	175.7(2)		

Symmetry transformations used to generate the equivalent atoms: #1:  $x, -y+1/2, z$ ; #2:  $-x+2, -y, -z+1$ ; #3:  $x-1/2, y, -z+3/2$ ; #4:  $x+1/2, y, -z+1/2$ ; #5:  $-x+3/2, -y, z-1/2$ ; #6:  $x-1/2, y, -z+1/2$ ; #7:  $-x+3/2, -y, z+1/2$ ; #8:  $x+1/2, y, -z+3/2$

**Table 2. Hydrogen Bond Lengths (Å) and Bond Angles (°) for Complex 1**

D–H...A	d(D–H)	d(H...A)	d(D...A)	<(DHA)
O(1w)–H(12)...O(7w)	0.84	2.30	2.855(2)	124
O(2w)–H(21)...O(5w) <sup>#1</sup>	0.84	2.39	2.917(2)	122
O(3w)–H(32)...O(7) <sup>#2</sup>	0.84	2.12	2.757(9)	132
O(4w)–H(41)...O(6w)	0.84	2.33	2.72(2)	109
O(4w)–H(42)...O(6w)	0.84	2.36	2.72(2)	106
C(10)–H(10A)...O(10)#3	0.96	2.45	3.143(1)	129
C(10)–H(10C)...O(12)	0.96	2.50	3.356(1)	149
C(16)–H(16C)...O(4)#4	0.96	2.53	3.363(1)	145
C(22)–H(22A)...O(8)#5	0.96	2.41	3.138(1)	133
C(22)–H(22B)...O(6)	0.96	2.44	3.334(1)	155


Symmetry codes: #1:  $1+x, y, z$ ; #2:  $2-x, -y, 1-z$ ; #3:  $-1/2+x, y, 3/2-z$ ; #4:  $1/2+x, y, 3/2-z$ ; #5:  $3/2-x, -y, -1/2+z$

### 3 RESULTS AND DISCUSSION

#### 3.1 Crystal structure of complex 1


Single-crystal X-ray analysis reveals that **1** crystallizes in orthorhombic system, space group *Pnma*. As shown in Fig. 1, the asymmetric unit of **1** comprises three Zn(II) ions, two Tm(III) ions, four H<sub>3</sub>mimda ligands, one bipy, three coordination water molecules and five lattice water molecules. The Zn(II) exhibits three kinds of coordination modes, among which Zn(1) and Zn(3) ions have the same coordination number. Zn(1) is connected with nitrogen atom N(2) and oxygen atom O(4) of one Hmimda<sup>2-</sup> ligand, and nitrogen atom N(5#3) and oxygen atom O(10#3) of another Hmimda<sup>2-</sup> ligand, as well as one oxygen atom O(4W) from the coordination water molecule. However, Zn(3) is coordinated by two nitrogen atoms N(4), N(7) and two oxygen atoms O(8), O(14) of two different H<sub>3</sub>mimda ligands, and one nitrogen atom (N8) from one bipy. Zn(2) is six-coordinated with nitrogen atoms (N1), N(3), N(6) and oxygen atoms O(2), O(6), O(12) from three different H<sub>3</sub>mimda ligands. There are two crystallographically unique Tm(III) centers in the asymmetric unit, which show different coordination environments. Tm(1) is seven-coordinated by six carboxylate oxygen atoms O(1), O(1#1), O(3), O(3#1), O(5), O(5#1) from three H<sub>3</sub>mimda, and one oxygen atom O(1W) from one coordinated water molecule in a pentagonal bipyramidal coordination geometry of TmO<sub>7</sub>. The Tm(1)–O<sub>carboxyl</sub> bond lengths vary from 2.212(7) to 2.256(7) Å and the Tm(1)–O<sub>water</sub> bond length is 2.361(10) Å. Tm(2) is eight-coordinated by five oxygen atoms O(7), O(9), O(11), O(13), O(13#1), O(14) from three H<sub>3</sub>mimda ligands and two other oxygen atoms O(2W), O3(W) from two coordinated water molecules, forming an

octahedral coordination geometry. The bond distances of Tm(2)–O range from 2.193(6) to 2.486(5) Å. The bond angles around each Tm(III) vary from 64.2(2) ° to 159.4(2) °. In addition, detailed hydrogen bonds of **1** are shown in Table 1, which all fall in the normal range of such weak interactions<sup>[22]</sup>.



**Fig. 1.** Coordination environments of Tm and Zn atoms in the asymmetric unit of **1**.

All H atoms and the noncoordinated water molecules are omitted for clarity



**Scheme 1.** Coordination modes of free H<sub>3</sub>mimda ligand in complex **1**

As indicated in Scheme 1, the mimda<sup>3-</sup> anions adopt both  $\mu_3$ -kN, O: kO, O': kN', O' and  $\mu_4$ -kN, O: kN', O'kO, O': kO'', O'' coordination modes connected with the adjacent Tm(III) and Zn (II) ions. Each TmO<sub>8</sub> connects two neighboring Zn(II) chelate units through two H<sub>3</sub>mimda ligands in two different modes to generate a 1D zigzag chain and further gives rise to a unique 2D Tm-Zn heteronuclear metal-organic network structure (Fig. 2b). In addition, six H<sub>3</sub>mimda ligands link the neighboring Zn(II) ions *via* N,O-chelating composed of a [Zn<sub>6</sub>(mimda)<sub>6</sub>] ring with the bipy just acting as a terminal ligand leaving a free N atom. The [Zn<sub>6</sub>(mimda)<sub>6</sub>] rings are connected by one H<sub>3</sub>mimda ligand to afford a 1D six-membered ring chain along the *b*-axis, as shown in Fig. 2c. The resultant 3D framework of **1** can be depicted as the Tm-Zn heteronuclear cages of [Tm<sub>10</sub>Zn<sub>10</sub>(mimda)<sub>12</sub>(bipy)<sub>2</sub>]<sub>n</sub> linked with (TmO<sub>7</sub>)<sub>n</sub> through H<sub>3</sub>mimda ligands of modes *a* and *b* (Fig. 3), and it is similar to other Ln compounds just reported<sup>[23]</sup>. In the Tm-Zn heteronuclear cage, [Zn<sub>6</sub>(mimda)<sub>6</sub>] and [Tm<sub>10</sub>(mimda)<sub>6</sub>]<sub>n</sub> are connected by H<sub>3</sub>mimda ligand, leading to a "interlock" structure unit. After the hypothetical removal of guest water molecules, the total potential solvent-accessible void is found for this 3D framework of **1** to be 2025.8 Å<sup>3</sup> per cell volume (accounting for 22.2% of the total unit cell system), calculated using the PLATON program<sup>[24]</sup>.




Fig. 2. (a) Schematic illustration of the 1D chain structure of 1 viewed along the *bc* plane; (b) Schematic illustration of the 2D interspersed structure of 1 viewed along the *ac* plane; (c) The bipy acts as a terminal ligand, leaving a free N atom, bridged at the  $[Zn_6(mimda)_6]$  ring ends along the *ab* plane





Fig. 3. 3D framework composed of Tm-Zn heteronuclear units 1 along the *ab* plane


### 3.2 Powder X-ray diffraction patterns and thermal stability





**Fig. 4. Simulated and experimental PXRD patterns of complex 1**

As shown in Fig. 4, powder X-ray diffraction pattern (PXRD) of complex **1** exhibits characteristic peaks at  $2\theta$  positions of 9.8, 12.2, 16.4, 18.3, 28.2°. The experimental pattern of complex **1** is basically consistent with the simulated one, indicating the phase purity of the synthesized bulk samples. Thermal gravimetric analysis (TGA) experiment was performed on a sample consisting of numerous single crystals from 30 to 1200 °C under N<sub>2</sub> atmosphere at a heating rate of 10 °C·min<sup>-1</sup>. The TG and DTA curves are depicted in Fig. 5. Complex **1** firstly undergoes weight loss of 5.1% at about 175 °C due to the release of eight water molecules (calcd. 5.4%), and the framework decomposes at about 260 °C attributed to the departure of bipy moieties 11.7% (calcd. 10.6 %). Complex **1** continues to break down upon further heating and exhibits an obvious weight loss of H<sub>3</sub>mimda ligands above 700 °C.

**Fig. 5. Thermal gravimetric analysis plot of complex 1**

### 3.3 Luminescence property

The luminescence properties of complex **1**, bipy and free H<sub>3</sub>mimda ligand were investigated in the solid state at room temperature. As illustrated in Fig. 6, complex **1** exhibits an emission band with the maximum at 476 nm upon excitation at 325 nm. However, the maximum emission wavelength of H<sub>3</sub>mimda ligand and bipy are 416 ( $\lambda_{\text{ex}} = 315$  nm) and 363 nm ( $\lambda_{\text{ex}} = 270$  nm), respectively. Compared with the free bipy and H<sub>3</sub>mimda ligands, luminescence is probably originated from the ligand emission. The enhancement and significant red shift of the emission occur in complex **1**, which is probably due to the reaction between free ligands and metal ions, and further form the skeleton structure<sup>[25-28]</sup>.




Fig. 6. Luminescent spectra of complex 1, bipy and H<sub>3</sub>mimda ligand

## REFERENCES

- (1) Li, J. R.; Sculley, J.; Zhou, H. C. Metal-organic frameworks for separations. *Chem. Rev.* **2011**, 112, 869–932.
- (2) Furukawa, H.; Cordova, K. E.; O’Keeffe, M.; Yaghi, O. M. The chemistry and applications of metal-organic frameworks. *Science* **2013**, 341, 1230444.1–1230444.12.
- (3) Stock, N.; Biswas, S. Synthesis of metal-organic frameworks (MOFs): routes to various MOF topologies, morphologies, and composites. *Chem. Rev.* **2012**, 112, 933–969.
- (4) Fang, Q. R.; Zhu, G. S.; Jin, Z.; Ji, Y. Y.; Ye, J. W.; Xue, M.; Yang, H.; Wang, Y.; Qiu, S. L. Mesoporous metal-organic framework with rare eth topology for hydrogen storage and dye assembly. *Angew. Chem.* **2007**, 119, 6758–6762.
- (5) Halper, S. R.; Do, L.; Stork, J. R.; Cohen, S. M. Topological control in heterometallic metal-organic frameworks by anion templating and metalloligand design. *J. Am. Chem. Soc.* **2006**, 128, 15255–15268.
- (6) Zhao, D.; Cui, Y. J.; Yang, Y.; Qian, G. D. Sensing-functional luminescent metal-organic frameworks. *Cryst. Eng. Comm.* **2016**, 18, 3746–3759.
- (7) (a) Feng, X.; Feng, Y. Q.; Chen, J. L.; Ng, S. W.; Wang, L. Y.; Guo, J. Z. Reticular three-dimensional 3d-4f frameworks constructed through substituted imidazole dicarboxylate: syntheses, luminescence and magnetic properties study. *Dalton. Trans.* **2015**, 44, 804–816. (b) Chen, J. L.; Feng, X.; Xie, S. Y.; Wang, C. L.; Wang, L. Y.; Lang, X. M. Synthesis, structure and characterization of a 3d-4f hetero-metallic complex based on imidazole-dicarboxylate. *Chin. J. Struct. Chem.* **2015**, 34, 771–776.
- (8) Zhou, R. S.; Shao, J.; Li, Y.; Song, J. F. Three new imidazole dicarboxylate metal compounds: synthesis, structures, and magnetic property. *Inorg. and Nano-Metal Chem.* **2017**, 47, 509–514.
- (9) Guo, M.; Chen, N.; Gao, Y. C.; Lu, H. J.; Li, G. A series of lanthanide-organic frameworks constructed by 2-methyl imidazole dicarboxylate and oxalate: synthesis, structures, and properties. *J. Coord. Chem.* **2012**, 65, 1724–1739.
- (10) Liu, X. W.; Guo, R.; Liu, H.; Yu, Y. Q.; Qi, X. W.; Xu, J. Y.; Xie, C. Z. Two series of novel 3D potentially porous heterometallic Cu-Ln coordination frameworks assembled by 3,4-pyridinedicarboxylic acid with different topologies and channels: syntheses, structures, luminescence and magnetic properties. *RSC Advances* **2015**, 5, 15059–15068.
- (11) Zhu, Y.; Wang, W. Y.; Guo, M. W.; Li, G.; Lu, H. J. An unprecedented 1-D mixed-valence Cu(II)/Cu(I) metal-organic framework bearing 2-phenyl imidazole dicarboxylates. *Inorg. Chem. Commun.* **2011**, 14, 1432–1435.
- (12) Kanoo, P.; Maji, T. K. Construction of a 2D rectangular grid and 3D diamondoid interpenetrated frameworks and their functionalities by changing the second spacers. *Eur. J. Inorg. Chem.* **2010**, 5, 3762–3769.
- (13) Jia, H. L.; Guo, M. W.; Ma, B.; Liu, Y.; Li, G. A novel 3-D cobalt-organic framework constructed by 2-ethyl-1H-imidazole-4,5-dicarboxylic acid and 4,4'-bipyridine. *Synth. React. Inorg. Met.-Org. Chem.* **2013**, 43, 1458–1464.
- (14) Zhang, J. W.; Li, X. L.; Kan, X. M.; Liu, Y.; Liu, B. Q. Solvent-induced copper-lanthanide heterometallic coordination polymers based on pyridine-2,3-dicarboxylic acid: Syntheses, structures, and electrochemical properties. *Inorg. Chim. Acta* **2016**, 447, 18–21.
- (15) Rocha, J.; Paz, A.; Filipe, A.; Shi, F. N.; Ananias, D.; Silva, N. J.; Trindade, T. Mixed-metal d-f phosphonate frameworks-photoluminescence and magnetic properties. *Eur. J. Inorg. Chem.* **2011**, 13, 2035–2044.
- (16) Feltham, H. L. C.; Clerac, R.; Powell, A. K.; Brooker, S. A tetranuclear, macrocyclic 3d-4f complex showing single-molecule magnet behavior. *Inorg. chem.* **2011**, 50, 4232–4234.



- (17) Zhang, Y.; Huang, L.; Miao, H.; Wan, H. X.; Mei, H.; Liu, Y.; Xu, Y. Hydrothermal synthesis, structure, and optical properties of two nanosized  $\text{Ln}_{26}\text{@CO}_3$  (Ln = Dy and Tb) cluster-based lanthanide-transition-metal-organic frameworks (LnMOFs). *Chem. Eur. J.* **2015**, 21, 3234–3241.
- (18) Sakamoto, M.; Manseki, K.; Ōkawa, H. *d-f* Heteronuclear complexes: synthesis, structures and physicochemical aspects. *Coord. Chem. Rev.* **2001**, 219, 379–414.
- (19) Sheldrick, G. M. *SHELXS97, Program for the Solution of Crystal Structure*. University of Göttingen, Germany **1997**.
- (20) Sheldrick, G. M. *SHELXL97, Program for the Crystal Structure Refinement*. University of Göttingen, Germany **1997**.
- (21) Feng, X.; Wang, J. G.; Liu, B.; Wang, L. Y.; Zhao, J. S.; Ng, S. K. From Two-dimensional double decker architecture to three-dimensional pcu framework with one-dimensional tube: syntheses, structures, luminescence, and magnetic studies. *Cryst. Growth Des.* **2012**, 12, 927–938.
- (22) Desiraju, G. R.; Steiner, T. *The Weak Hydrogen Bond in Structural Chemistry and Biology*. Oxford University Press: Oxford **1999**.
- (23) Feng, X.; Feng, Y. Q.; Guo, N.; Sun, Y. L.; Zhang, T.; Ma, L. F.; Wang, L. Y. Series *d-f* heteronuclear metal-organic frameworks: color tunability and luminescent probe with switchable properties. *Inorg. Chem.* **2017**, 56, 1713–1721.
- (24) Spek, A. L. PLANT. An integrated tool for the analysis of the result of a single crystal structure determination. *Acta Crystallogr., Sect A* **1990**, 46, C34–C34.
- (25) Fomina, I.; Dobrokhotova, Z.; Aleksandrov, G.; Emelina, A.; Bykov, M.; Malkerova, I.; Bogomyakov, A.; Puntus, L.; Novotortsev, V.; Eremmenko, I. Novel 1D coordination polymer  $\{\text{Tm}(\text{Piv})_3\}_n$ : synthesis, structure, magnetic properties and thermal behavior. *J. Solid State Chem.* **2012**, 185, 49–55.
- (26) Tian, G.; Zhu, G.; Fang, Q.; Guo, X.; Xue, M.; Sun, J.; Qiu, S. L. Design, synthesis and fluorescence of two-dimensional pillared layers by connecting infinite one-dimensional chains via 4,4'-bipyridine. *J. Mol. Struct.* **2006**, 787, 45–49.
- (27) Cui, Y.; Yue, Y.; Qian, G.; Chen, B. Luminescent functional metal-organic frameworks. *Chem. Rev.* **2011**, 112, 1126–1162.
- (28) Li, X.; Wang, X. W.; Zhang, Y. H. Blue photoluminescent 3D Zn(II) metal-organic framework constructing from pyridine-2,4,6-tricarboxylate. *Inorg. Chem. Commun.* **2008**, 11, 832–834.

## A Three-dimensional Tm(III)-Zn(II) Heteronuclear Metal-organic Framework Based on Imidazole-dicarboxylate Ligand: Synthesis, Crystal

## Structure and Luminescence Property

GUO Nan(郭楠) FENG Xun (冯勋) JIA Hong(贾红)

QIN Guo-Zhan(秦国展) WEI Jing-Tao(魏靖涛) HAN Zhi-Yue(韩志越)

A *d-f* heteronuclear metal-organic framework (MOF),  $\{[\text{TM}_3\text{Zn}_6(\text{bipy})_2(\text{mimda})_7(\text{H}_2\text{O})_3](\text{H}_2\text{O})_5\}_n$  (**1**,  $\text{H}_3\text{mimda}$  = 2-methyl-1-H-imidazole-4,5-dicarboxylic acid, and  $\text{bipy}$  = 4,4'-bipyridine), has been synthesized under solvothermal conditions, and structurally characterized by elemental analysis, IR spectra and X-ray single-crystal diffraction.

